

propylene copolymer, wherein the amount of said maleic anhydride added to said starting material is about 0.1% to about 25 wt % of said starting material.

2. (Currently Amended) A composition comprising the emulsible polyolefin wax of claim 1.
3. (Currently Amended) The composition of claim 2, wherein said emulsion light transmittance is at least about ~~3~~50%.
4. (Canceled).
5. (Currently amended) The composition of claim 4 2, wherein said emulsible polyolefin ~~maleated polypropylene~~ wax has a Mw of about 10,000 to about 20,000, and a melt viscosity of about 200 to about 800 cps, ~~and an emulsion light transmittance of at least about 50%.~~
6. (Original) A floor polish comprising the composition of claim 1.
7. (Original) A floor polish comprising the composition of claim 2.
8. (New) The emulsible polyolefin wax of claim 1, wherein said emulsible polyolefin wax has a saponification number of about 20 to about 150 KOH/g.
9. (New) The emulsible polyolefin wax of claim 1, wherein said wax has a Gardner color index of no greater than about 8.
10. (New) The emulsible polyolefin wax of claim 1, wherein said wax has a Gardner color index of no greater than about 7.